

## AEROSIL® fumed silica for dental composites



**AEROSIL® fumed silica increase the hardness and abrasivity resistance of dental composites. In addition, they reduce the edge gap that can occur when the composite is cured.**

A high filler content can be achieved with unmodified hydrophilic AEROSIL® fumed silica grades as well as by surface modified types. AEROSIL® fumed silica are white powders with high purity, which do not impair the optical properties of the resulting dental composites.

### Characteristic physico-chemical data

Properties and test method	Unit	AEROSIL® OX 50	AEROSIL® R 709	AEROSIL® R 711	AEROSIL® R 7200
<b>Specific surface area (BET)</b>	m <sup>2</sup> /g	35–65	25–45	125–175	125–175
<b>pH value</b> in 4% dispersion	–	3.8–4.8	4.5–7.5	4.0–6.0	4.0–6.0
<b>Loss on drying</b>	%	≤ 1.5	≤ 2.5	≤ 1.5	≤ 1.5
<b>Carbon content</b>	%	–	1.5–3.5	4.5–6.5	4.5–6.5
<b>Tamped density</b>	g/L	approx. 100	approx. 130	approx. 60	approx. 230
<b>SiO<sub>2</sub> content</b> based on ignited material	%	≥ 99.8	≥ 99.8	≥ 99.8	≥ 99.8

The given values are typical data, specifications on request.



## Benefits of AEROSIL® fumed silica in dental composites

**AEROSIL® OX 50** is a hydrophilic silica, consisting of particles with low surface area and thereby barely affects the rheology of the composite.

AEROSIL® fumed silica can be functionalized by a treatment of the hydrophilic surface. One class of these AEROSIL® fumed silica grades with modified surface chemistry bears methacrylate groups. These functional groups are ideal to crosslink in the polymerization reaction of the composite.

**AEROSIL® R 709** has a marginal influence on the rheology due to its low surface area.

**AEROSIL® R 711** has a thickening effect. The rheology of the monomer solution may be adjusted by adding this product.

**AEROSIL® R 7200** can control the rheology of the formulation. It has an improved incorporation behavior and increased processability.



AEROSIL® fumed silica | for dental composites | 07-16

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND / OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and / or recommendations at any time, without prior or subsequent notice.

AEROSIL® is a registered trademark of Evonik Industries or one of its subsidiaries.

### Europe/Middle-East/ Africa/Latin America

**Evonik Resource Efficiency GmbH**  
Business Line Silica  
Rodenbacher Chaussee 4  
63457 Hanau  
Germany

PHONE +49 6181 59-12532  
FAX +49 6181 59-712532  
ask-si@evonik.com

### North America

**Evonik Corporation**  
Business Line Silica  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA

PHONE +1 800 233-8052  
FAX +1 973 929-8502  
ask-si-nafta@evonik.com

### Asia Pacific

**Evonik (SEA) Pte. Ltd.**  
Business Line Silica  
3 International Business Park  
#07-18, Nordic European Centre  
Singapore 609927

PHONE +65 6 809-6877  
FAX +65 6 809-6677  
ask-si-asia@evonik.com

www.aerosil.com

Evonik. Power to create.

